



DETALE CPH is a line of exclusive decorative products to take care of the [□] small details. Paints and finishes are inspired by our Nordic design heritage and the changeability of nature. The products are suitable for professional as well as do-it-yourself use.

Properties

Decorative treatment for indoor surfaces. Included in the KABRIC Floor treatment system. Produces a vibrant, textured surface. The choice of the associated Prepare and Strongcoat is decisive for the function and properties of the treatment.

- **Decorative**
- **Changing**
- **Rustic**

Use

The substrate must be primed with KABRIC Floor Smooth Prepare or KABRIC Floor Prepare. Finish treatment with KABRIC Floor Strongcoat or KABRIC Floor Strongcoat Extra. The choice of Prepare and Strongcoat will determine the area of use for the treatment.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

KABRIC Floor Prepare is used for priming even surfaces. Any markings from the substrate may be visible in the finished surface.

KABRIC Floor Smooth Prepare is used for priming where unevenness and markings from the substrate are not desired in the finished surface.

Apply 2 thin, covering layers.

Sand or scrub away any unevenness between the two layers.

For an extra soft finish, re-sand the surface after the 2nd layer.

Finish with KABRIC Floor Strongcoat or KABRIC Floor Strongcoat Extra.

Application

Stir the product to a uniform consistency.

Apply and distribute the product evenly using a wide spatula, apply wet-on-wet in a thin layer.

Decide on your mode of application according to the desired finish.

Turn off floor heating while treatment is underway.

After treatment, increase the floor heating gradually.

Cold/heat can affect the viscosity of the material.

Avoid condensation formation.

Cold and increased humidity extend drying time, full curing and recoating interval.

Increased temperature and low atmospheric humidity reduce drying time and full curing.

Always do a treatment test to check acceptance of adhesion and result.

Expected result

Smooth out changing surfaces for additional treatment.

Unevenness from the substrate may be visible in the finished surface.

Moisture-related size changes from the substrate can result in visible markings in the finished surface.

Environmental information

Clean off the paint from tools before cleaning. Bring remains of fluent paint to the local recycling centre. Minimize your paint waste by pre-estimating how much paint you need. Keep the leftover paint for future use so you can effectively reduce the environmental impact.

Storage: Cool, frost free and tightly closed

Protection equipment: Painting: eye protection, gloves. Sanding: respiratory protection.

Technical Data

Nominal spreading rate (m ² /ltr.)	3
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	2
Recoatable at 20° C, 60 % RH (Hours)	5
Fully cured at 20° C, 60 % RH (Days)	5
Cleaning of Tools etc.	Water

Current TDS Version

July 2021